

TECNO PIEMONTE S.p.A.

CENTRO PROVE – RICERCHE – AMBIENTE – SERVIZI PER INGEGNERIA
AUT. MIN.: INTERNO - SALUTE - SVILUPPO ECONOMICO – ISTRUZIONE UNIVERSITA' E RICERCA
INFRASTRUTTURE E TRASPORTI ART. 20 LEGGE 1086/71 – DPR. 380/01
INDAGINI – GEOTECNICA TERRENI E ROCCE - MARCATURA CE ORGANISMO NOTIFICATO N° 1372



Customer: **Imper Italia S.r.l.**
Via Volta, 8
10071 Fraz. Mappano
Borgaro (TO)

TEST REPORT N° 02622/43/56 of 22/03/2017

Page 1 of 2

Order n° **403/IM** of **10-mar-17** Your ref: -

SETTORE MATERIALS FOR WATERPROOFING

PROPERTY OR CONTRACTING INSTITUTION:

SITE:

SAMPLING METHOD:

SAMPLING REPORT:

RULES OF SAMPLING:

SAMPLING DATE:

SAMPLE RECEPTION DATE:

ORIGIN OF THE SAMPLE:

SAMPLING POINT:

TYPE OF THE SAMPLE:

MARK OF THE SAMPLE:

Our SAMPLE RECORD:

LEGISLATION REFERENCE:

-
Production plant of Marano Ticino (NO)
Customer care and responsibility
-
Customer care and responsibility
Not declared
10/03/2017
Production plant of Marano Ticino (NO)
-
PVC waterproofing membrane
EUROFLEX V AT 1,2 mm thickness
403_1
D.M. 21/03/1973 G. U. Suppl. Ordin. n° 104
of 20/04/1973
General rules - Packaging and materials destined
to come into contact with food and beverages
Determination of Global Migration

Results relate only to tested samples

LABORATORY DIRECTOR

Dott. Irene SBERNA

ANALYST


P.I. Paolo BUONAVITA

SEDE AMM. / OPERATIVA:
Statale Valsesia, 20
13035 Lenta (Vc)

SEDE LEGALE:
Via C. Pizzorno, 12
28078 Romagnano Sesia (No)

UNITÀ LOCALI:
13836 Cossato (Bi) - Via Corridoni, 54
00161 Roma - Via De Rossi, 4


Tel. +39 - 0163.885.111 - Fax. +39 - 0163.885.028 - E-mail: tecnopiemonte@tecnopiemonte.com - www.tecnopiemonte.com
P. IVA 00590090031 - R.E.A. NO 136553 - CAP. SOC. a 2.400.000,00 I.V. - TRIB. NO 7192



TEST REPORT N° 02622/43/56 of 22/03/2017						Page 2 of 2	
Verbal of acceptance n° 403/IM of 10-mar-17						Your ref.	
Parameter	Result	Limit ⁽¹⁾	U.M.	Test method	Starting date analysis	End date analysis	Note
ANALISI							
M (Global Migration)	<0,1	60,0	mg/kg	D.M. 21/03/1973 G.U. Suppl. Ordin. n° 104 of 20/04/1973 All. IV sez. I Met. B	13/03/2017	14/03/2017	*
	<0,6	10,0	mg/dm ²				

The limit values taken as reference are those reported in D.M. 21/03/73 titolo II Art. 9bis

*: s a result of static contact for 24 hours at 40 ° C, with solvent simulating distilled water



ANNEX TO TEST REPORT N. 02622.43.56 OF 22/03/2017

Analytical results for the sample “EUROFLEX V AT 1,2 mm thickness”, delivered by Imper Italia S.r.l. to TECNO PIEMONTE S.p.A. laboratory on 10/03/2017, with our verbal acceptance n. 403/IM/17 del 10/03/2017, limited to the analyzed parameters, it results to be conform to limits of the Ministerial Act 21/03/1973 G. U. Suppl. Ordin. n° 104 of 20/04/1973, regarding the Global Migration.

Pagina 1 di 1